



ENAPART



93 S Railroad Avenue Unit C
Bergenfield NJ 07621 USA
www.enapart.com
sales@enapart.com



Via del Canneto 35,
Borgosatollo, Brescia - Italia
www.enapart.it
vendite@enapart.it



Barbaros Mah. Ihlamur Bul. Aĝaoĝlu
My Newwork No:3/15 Ataşehir / İstanbul
www.enapart.net
satis@enapart.net



PRIVADA 10 B SUR #3908 COL.
ANZUREZ, C.P. 72530, PUEBLA, PUE
www.enapart.com.mx
sales@enapart.com.mx



Friedrich-Ebert-Anlage 36, 60325
Frankfurt am Main, Germany
www.enapart.de
anfrage@enapart.de



4 boulevard Carnot, 95400
villiers-le-bel, Paris, France
www.enapart.fr
sales@enapart.fr



65049, ОДЕСА, ВУЛИЦЯ ІВАНА
ФРАНКА, БУДИНОК 55, ПОВЕРХ 3
www.enapart.com.ua
sales@enapart.com.ua



MUNICIPIUL BUCUREȘTI, SECTOR 3,
B-DUL BASARABIA, NR.250, CORP P+5
www.enapart.ro
sales@enapart.ro



〒584-0023 大阪府富田林市若松町
東2丁目2番16号
www.enapart.co.jp
sales@enapart.co.jp



PLAZA NUESTRA SEÑORA DE LAS
NIEVES 12 ,LOCAL ,50012,ZARAGOZA
www.enapart.es
ventas@enapart.es



Складова база „Онгъл“, Склад А2, п.к.
4006, гр. Пловдив, България
www.enapart.bg
sales@enapart.bg



3 Austin Mews, High Street, Hemel
Hempstead, HP1 3AF , United Kingdom
www.enapart.co.uk
sales@enapart.co.uk

ISOSCOPE[®] MPOR

Pocket Instrument with PC-Interface for
Convenient and Fast
Coating Thickness Measurement on
Virtually all Non-Ferrous Metals



Description

Instrument properties	<p>The ISOSCOPE measuring instrument measures coating thicknesses easily, quickly, non-destructively and with the precision that is typical for all Fischer instruments.</p> <ul style="list-style-type: none">• Ideal for onsite applications due to the compact size, the light weight and the robust and durable instrument design• Intuitive operation of the menu navigation and graphic display. The display turns automatically, like a smart phone• Second display for reading the measurement results directly on the top side of the instrument, e.g., for measuring overhead• Different languages are selectable• Manufacturer's certificate, included in the scope of supply
Generating measurements	<ul style="list-style-type: none">• The specimen's shape and permeability have a comparatively low influence on the measurement results• Patented conductivity compensation for measurements on non-magnetic substrate materials• Two special measuring modes in accordance with the measurement regulations IMO PSPC (90/10-Rule) and SSPC-PA2

Applications

Examples	<p>Nonferrous metal substrates (NF)</p> <ul style="list-style-type: none">• Paint, varnish or plastic coatings on aluminium, copper or brass• Anodized coatings on aluminium <p>The instrument is particularly suited for highly precise measurements of thin coatings.</p>
----------	---

Evaluation

Statistics	Display of mean value, standard deviation, MIN, MAX and number of measurements per block
PC software included in the scope of supply	PC software FISCHER DataCenter with the following functionality: Transferring and archiving measurement data, comprehensive statistical and graphical evaluations, easy creation and printing of inspection reports

Measuring Modes

Standard (Std)	Standard measuring mode for simple, universal coating thickness measurements, all measurement functions are available.
IMO PSPC 90/10 (90.10)	90/10 rule stored in the instrument for coating thickness measurements according to the requirements of the "Performance Standard for Protective Coatings" of the International Maritime Organization (IMO PSPC).
SSPC-PA2 (SSPC)	Coating thickness measurement according to the test specification SSPC-PA2 of the Society for Protective Coatings (SSPC).

Measurement Functions

Block size	Adjustable between 2 and 20 single readings per block
Tolerance limits	Adjustable, depending on the selected measuring mode
Offset value	In the standard mode, the freely adjustable offset value is deducted automatically from the measured value. Thus, one obtains the thickness of the top coating if for instance the interim coating is known.
Units of measurement	Selectable μm or mils
Continuous display mode	Measurement in "continuous display mode" for continuous sampling of the surfaces, e.g., in the manufacture of tanks and containers.
Normalization	Adaptation to the substrate material and the shape of the specimen.
Calibration	<p><i>Factory calibration</i></p> <p>Each individual instrument is factory calibrated at several reference points with the greatest care to ensure the highest possible degree of trueness.</p> <p><i>Corrective calibration (Adjustment)</i></p> <p>Adaptation to the substrate material and the shape of the specimen and to a thickness value using a calibration foil.</p> <p><i>Simple Calibration</i></p> <p>Adaption to the coating and substrate material in one step using a coated reference part with a coating thickness higher than 200 μm (7.87 inches). Nevertheless, this kind of calibration supplies only a lower accuracy as specified in the sections Trueness and Repeatability Precision.</p>

General Features

Measuring method	Eddy current method (ISO 2360, ASTM D7091, Measurement of non-conductive coatings on non-magnetic substrate metals)
Probe	Probe tip radius: 1.2 mm (46.8 mils); Probe tip material: Ruby
Data memory	Max. 10,000 individual readings; the contents of the memory is retained even without batteries
Measuring frequency	More than 70 measurements per minute
Measurement acquisition	Automatic upon placement of the probe; indication of the measurement with a beep visually with a green lit LED
Display limit value violation	Acoustically through 2 short beeps and visually with a red lit LED
Display	<ul style="list-style-type: none">• Graphic display with an automatically turning display in order to read the measurement results in many different instrument positions• LCD display on the top side of the instrument, e.g., for reading the measurement value for measuring overhead
Languages	Many different display languages are selectable: German, English and several other European and Asian languages
USB port	2.0 compatible, for connecting a PC
Data transfer	Single readings, mean values, group separator
Admissible ambient temperature range during operation	0 +40 °C (+32 ... +104 °F)

ISOSCOPE® MPOR

Weight (incl. batteries)	137 g (4.8 oz)
Power supply	2 Batteries, LR6, AA, 1.5 V
Dimensions (W x D x H)	Width: 64 mm (2.5 "); depth: 28 mm (1.1 "); height: 85 mm (3.35 ")

Measurement Range

0 ... 1200 μm (46.8 mils)

Trueness

based on factory calibration standards of the Helmut Fischer GmbH	0 ... 70 μm : $\leq 1.0 \mu\text{m}$	0 ... 2.7 mils: ≤ 0.039 mils
	70 ... 250 μm : $\leq 1.5 \%$ of reading	2.7 ... 9.75 mils: $\leq 1.5 \%$ of reading
	250 ... 1000 μm : $\leq 3 \%$ of reading	9.75 ... 39 mils: $\leq 3 \%$ of reading

Repeatability Precision

based on factory calibration standards of the Helmut Fischer GmbH, 5 single measurement readings on each standard	0 ... 50 μm : $\leq 0.25 \mu\text{m}$	0 ... 2 mils: ≤ 0.0098 mils
	50 ... 1000 μm : $\leq 0.5 \%$ of reading	2 ... 39 mils: $\leq 0.5 \%$ of reading

Ordering Data

605-116	ISOSCOPE MPOR, probe integrated in the measuring instrument
---------	---

Scope of Supply

Instrument case; protective instrument cover; lanyard; 2 batteries; metal plate ISO/NF for testing purposes; calibration foil (foil thickness about 75 μm (2.95 inches)); operator's manual; manufacturer's certificate; USB cable; support CD with USB drivers, software program FISCHER DataCenter for convenient evaluating, documenting and archiving of the measurement data, software program PC-Datex for exporting the measurement data to an Excel spreadsheet

ISOSCOPE® is a registered trademark of Helmut Fischer GmbH Institut für Elektronik und Messtechnik in Germany and in other countries.